INSTALLATION GUIDE: BRICK, BLOCK & STONE

Breathaplasta can be applied directly to brick, block and stone and is compatible with all masonry applications. Breathaplasta is a quick and easy lime plaster. It's simple to use and sets within an hour.

Important notes for use on brick, block and stone:

- Ensure the masonry is consolidated. Dub out the masonry if needed fill holes and level off.
- Mist the surface of the masonry 10-15 mins prior to plaster application to control suction.
- Allow 1 hour to dry per 2mm of plaster thickness.



Add 1 x 20kg bag of Breathaplasta to approx. 10 - 11 litres of clean water

Mix 60
Time seconds

Mix the plaster using a paddle mix for at least 60 seconds



Mist the masonry surface with clean water to control suction



Apply at least 2 coats of plaster to all surfaces.

Each coat should be up to 10mm thick



Setting time per coat of Breathaplasta is approx.
45 - 60 minutes



Run a clean trowel over the surface of the plaster for a smooth finish. Use a sponge float for more textured finishes

breath Aplasta











Equipment Required:

Breathaplasta, clean water and brush or water mister, hawk, trowel and plastering tools.

Surface preparation:

Consolidate wall to ensure no loose material. Surface should be uniformly flat. Mist the masonry surface with water to control suction.

Recommended plaster thickness:

Up to 50mm total thickness.

Recommended plaster application:

- 1. Base coat/scratch coat 4-10mm.
- Additional coats up to 10mm thick to a max depth of 50mm. Allow approximately 1 hour to dry per 2mm thickness of plaster.
- 3. Top coat approx. 4mm. Moisten top coat using a fine mist spray bottle to help trowel to a smooth finish.

Coverage per 20kg bag:

Approx. 5 square metres at 4mm thickness

Setting time per coat:

Approx. 45 - 60 minutes



BUILDING HIGH PERFORMANCE WITH BIO MATERIALS